



## SOLVENT BASED RESIN

### TUNASKYD LONG OIL ALKYD

TUNASKYD PRODUCT CODE	OIL TYPE	OIL CONTENT (%)	PA CONTENT (%)	SPECIFICATION				SOLVENT	PERFORMANCE	APPLICATION
				Solids Content (%)	Acid Value mg KOH/g (max)	Viscosity (25°C) Pra Tube No.	Colour Gardner (max)			
8604-70	Soya	64	25	70 ± 1	10	65% 17 – 19	5	White Spirit	Fast dry, high viscosity, good gloss & gloss retention, good hardness – flexibility balance, good brush ability	Architectural paint, marine paint, air drying paint, structure steel paint, and varnish
8608-70	SOFA	62	25	70 ± 1	10	65% 17 – 18	5	White Spirit	Fast dry, good colour & yellowing resistance, good gloss & gloss retention, good hardness – flexibility balance	
8609-70	SOFA	62	24	70 ± 1	3 - 8	70% 15 – 17	4	White Spirit	Fast dry, good colour & yellowing resistance, good gloss & gloss retention, good hardness – flexibility balance	
8611-70	Soya	64	25	70 ± 1	10	70% 17 – 18	5	White Spirit	Fast dry, good colour & yellowing resistance, good gloss & gloss retention, good hardness – flexibility balance	
8614-70	Soya	64	25	70 ± 1	10	70% 15 – 16	4	White Spirit	Fast dry, good colour & yellowing resistance, good gloss & gloss retention, good hardness – flexibility balance	
8615-70	Soya	64	25	70 ± 1	10	70% 14 – 15	3	White Spirit	Low viscosity, Fast dry, good colour & yellowing resistance, good gloss & gloss retention, good hardness – flexibility balance	