



SOLVENT BASED RESIN

TUNASKYD MEDIUM OIL ALKYD

TUNASKYD PRODUCT CODE	OIL TYPE	OIL CONTENT (%)	PA CONTENT (%)	SPECIFICATION				SOLVENT	PERFORMANCE	APPLICATION
				Solids Content (%)	Acid Value mg KOH/g (max)	Viscosity (25°C) Pra Tube No.	Colour Gardner (max)			
4601-60	Soya	50	33	60 ± 1	10	50% 17 – 19	4	White Spirit	Good durability, good gloss, good yellowing resistance & colour retention, high viscosity	Architectural paint, industrial primer & finish and structural steel paint
4602-50	Soya	47	32	50 ± 1	10	50% 15 – 16	4	White Spirit	Fast dry, good durability, good yellowing resistance & colour retention	
4609-55	SOFA	49	29	55 ± 1	8	55% 16 – 17	6	White Spirit	Fast dry, good durability, good yellowing resistance & colour retention	
4611-60	SOFA	49	29	60 ± 1	8	50% 15 – 16	4	White Spirit	Fast dry, excellent gloss, good durability, good yellowing resistance & colour retention	
4613-60	SOFA	42	31	60 ± 1	10	50% 18 – 20	3	White Spirit	Fast dry, good durability, good yellowing resistance & colour retention, high viscosity	